

CRYSTAL-R UV

Resina Poliester Transparente para curado con lámparas UV.
Transparent Polyester Resin for curing with UV lamps.

PROPIEDADES / PROPERTIES





Resina Cristalina para Piedra. Formulada especialmente para resinar la cara de tablas o losas de piedra.

Crystalline Stone Resin. Specially formulated to resinate the face of stone slabs.



Ref. 092408

MATERIALES / MATERIALS	COLORES / COLOURS	SECTOR / SECTOR
✓ MÁRMOL / MARBLE	Crystal 	INDUSTRIA MÁRMOL MARBLE INDUSTRY

ENVASE / CONTAINER	€/ UD.	UD./BOX
	Crystal UV	
1 Kg / 900 ml	Consultar / Consult	 12
5 Kgs / 4,5 L	Consultar / Consult	 4
20 Kgs / 18 L	Consultar / Consult	 1
1000 Kgs / 900 L	Consultar / Consult	 1

USO / USE



Aplicación horizontal
Horizontal application



Uso en interior
y exterior
Indoor and
outdoor use



Material de
consistencia líquida
Material of liquid
consistency

LÍQUIDO



Antes de su aplicación se recomienda mezclar con 1% de secante líquido, para conseguir un endurecido perfecto. Posteriormente aplicar sobre la piedra y radiar con luz ultravioleta para un curado perfecto.

Before application it is recommended to mix with 1% liquid siccative, to achieve a perfect hardening. Subsequently apply on the stone and radiate with ultraviolet light for a perfect curing.



5-10min 25°C

Tiempo que tarda el pegamento, masilla o resina en cambiar su viscosidad y comenzar su endurecido, una vez mezclado con el endurecedor.

Time it takes for the glue, putty or resin to change its viscosity and start hardening, once it has been mixed with the hardener.



30-35min 25°C

Tiempo que tarda el pegamento, masilla o resina en endurecer completamente una vez mezclado con el endurecedor. En este momento se puede manipular o lijar con total garantía.

Time it takes for the glue, putty or resin to harden completely once it has been mixed with the hardener. At this time it can be handled or sanded with total guarantee.



Protección
rayos UV
UV Protect

* Los ensayos se han realizado a una temperatura ambiente de 25°C.
* The tests have been carried out at an ambient temperature of 25°C.





CRYSTAL-R UV

RESINA
CRISTALINA PARA
PIEDRA

Producto Destinado a uso profesional **PRO**

MODO DE EMPLEO:

Antes de su aplicación, se recomienda mezclar con un 1% de secante líquido, para conseguir un endurecido perfecto. Posteriormente aplicar sobre la piedra y radiar con luz ultravioleta para curado perfecto.



Teléfono de urgencias de la sociedad: Tel. (+34) 965112713 Horario (UTC +1): L-V 7:00 a 15:00h. Para cualquier uso no descrito en la etiqueta consulte al departamento técnico de ABR Surface Technologies. Hoja de datos de seguridad a disposición del usuario que lo solicite.

Lote:

5Kg 4,5L
Cantidad Neta



www.abr-st.com

CRYSTAL-R UV

CRYSTAL
RESIN
FOR STONE

Product Destined to professional use **PRO**

METHOD OF USE:

Before application, it is recommended to mix with 1% liquid siccative to achieve a perfect hardening. Subsequently apply on the stone and radiate with ultraviolet light for perfect curing.



Emergency telephone number of the company:

Tel. (+34) 965112713 Opening hours (UTC +1): M-F 7:00 to 15:00h. For any use not described on the label, please consult the technical department of ABR Surface Technologies. Safety data sheet available on request.

Lote:

5Kg 4,5L
Net Weight



www.abr-st.com