

CRYSTAL-R CRYSTAL-R

Resina Cristalina para Piedra
Crystal Resin for Stone

PROPIEDADES / PROPERTIES





Resina Cristalina para Piedra. Formulada especialmente para resinar la cara de tablas o losas de piedra.

Crystalline Stone Resin. Specially formulated to resinate the face of stone slabs.



Ref. 092407

MATERIALES / MATERIALS	COLORES / COLOURS	SECTOR / SECTOR
✓ MÁRMOL / MARBLE	Crystal 	INDUSTRIA MÁRMOL MARBLE INDUSTRY

ENVASE / CONTAINER	€/ UD.	UD./BOX
	Crystal	
Kit: 1 Kg / 900 ml + 20 gr Secant	19,20	 12
Kit: 5 Kgs / 4,5 L + 100 gr Secant	53,31	 4
20 Kgs / 18 L	168,25	 1
1000 Kgs / 900 L	7200,00	 1

USO / USE ▼



Aplicación horizontal
Horizontal application



Uso en interior
y exterior
Indoor and
outdoor use



Material de
consistencia líquida
Material of liquid
consistency



2-3%

Antes de su aplicación, precisa ser
mezclado con 2-3% de secante líquido,
para conseguir un endurecido perfecto.
Before application, it needs to be
mixed with 2-3% liquid secant,
to achieve a perfect hardening.



5-10min 25°C

Tiempo que tarda el pegamento,
masilla o resina en cambiar su
viscosidad y comenzar su endurecido,
una vez mezclado con el endurecedor.
Time it takes for the glue, putty or resin
to change its viscosity and start
hardening, once it has been mixed with
the hardener.



30-35min 25°C

Tiempo que tarda el pegamento, masilla
o resina en endurecer completamente
una vez mezclado con el endurecedor.
En este momento se puede manipular
o lijar con total garantía.

Time it takes for the glue, putty or resin
to harden completely once it has been
mixed with the hardener.
At this time it can be handled or sanded
with total guarantee.

* Los ensayos se han realizado a una temperatura ambiente de 25°C.

* The tests have been carried out at an ambient temperature of 25°C.



www.abr-st.com





CRYSTAL-R

RESINA
CRISTALINA PARA
PIEDRA

Producto Destinado a uso profesional

PRO

MODO DE EMPLEO:

Antes de su aplicación, precisa ser mezclado con 2-3% de secante líquido, para conseguir un endurecido perfecto.



Teléfono de urgencias de la sociedad: Tel. (+34) 965112713 Horario (UTC +1): L-V 7:00 a 15:00h. Para cualquier uso no descrito en la etiqueta consulte al departamento técnico de ABR Surface Technologies. Hoja de datos de seguridad a disposición del usuario que lo solicite.

Lote:

5Kg 4,4L
Cantidad Neta



www.abr-st.com



CRYSTAL-R

CRYSTAL
RESIN
FOR STONE

Product Destined to professional use

PRO

METHOD OF USE:

Before application, it needs to be mixed with 2-3% liquid siccative to achieve a perfect hardening.



Emergency telephone number of the company:

Tel. (+34) 965112713 Opening hours (UTC +1): M-F 7:00 to 15:00h. For any use not described on the label, please consult the technical department of ABR Surface Technologies. Safety data sheet available on request.

Lot:

5Kg 4,4L
Net Weight



www.abr-st.com